
CREATON[®] No. 24

Chemical analysis:

SiO ₂	65,6 %
Al ₂ O ₃	23,0 %
TiO ₂	1,4 %
Fe ₂ O ₃	0,9 %
CaO	2,7 %
MgO	1,3 %
K ₂ O	2,8 %
Na ₂ O	2,3 %

Ceramic data:

Dry shrinkage in %:

7

Firing temperatur:

1070 °C

1140 °C

firing colour

white

pale

Firing shrinkage in %

4

6

Water absorption in %

7

1

**Coefficient of Thermal
Expansion (CTE):**

pre fired at
1000 °C

20 °C - 400 °C

67

20 °C - 500 °C

69

20 °C - 600 °C

80

CTE * 10⁻⁷/K